



REFRACTORY

2500° CAST	
2300° CAST	
2300° BOARD	
1200° BLOCK	

- REQUIREMENTS
- W - 1.7 GPM AT 45 PSI
 - G - 2,000,000 BTU'S AT 11" WC LIQUID PROPANE
 - E - 120V 15A 60HZ 1PH SUPPLY

THIS CONCEPTUAL DRAWING IS PROVIDED TO ILLUSTRATE BASIC DESIGN AND APPROXIMATE OVER ALL DIMENSIONS.

THIS DRAWING IS PROPRIETARY INTELLECTUAL PROPERTY OF GUSPRO INC. AND IS NOT TO BE REPRODUCED OR DISTRIBUTED IN ANY MANNER WITHOUT THE EXPRESSED WRITTEN PERMISSION OF GUSPRO INC.

	OVEN NO.	DATE
	GO-727272	6/JUN/00
CUSTOMER'S NAME		
CUSTOMER'S ADDRESS		
DRAWN BY	APPROVED BY	REVISION DATE
R.D.H.	J.M.S.	19/JAN/04